

(19)



Europäisches Patentamt
Eur p an Patent Office
Office européen des brevets



(11) Publication number:

0 622 429 A2**EUROPEAN PATENT APPLICATION**

(12)

(51) Int. Cl.⁵: **C09D 11/00, B41J 2/01**(21) Application number: **94106082.4**(22) Date of filing: **19.04.94**

(30) Priority: **26.04.93 JP 99527/93**
26.04.93 JP 99528/93
10.05.93 JP 108233/93
18.05.93 JP 116077/93

(43) Date of publication of application:
02.11.94 Bulletin 94/44

(84) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IE IT LI LU NL
PT SE

(71) Applicant: **CANON KABUSHIKI KAISHA**
30-2, 3-chome, Shimomaruko,
Ohta-ku
Tokyo (JP)

(72) Inventor: **Kashiwazaki, Akio, c/o Canon**
Kabushiki Kaisha




3-30-2, Shimomaruko,
Ohta-ku
Tokyo (JP)
Inventor: **Suga, Yuko, c/o Canon Kabushiki**
Kaisha

3-30-2, Shimomaruko,
Ohta-ku
Tokyo (JP)
Inventor: **Takaide, Aya, c/o Canon Kabushiki**
Kaisha
3-30-2, Shimomaruko,
Ohta-ku
Tokyo (JP)

(74) Representative: **Blumbach Weser Bergen**
Kramer Zwirner Hoffmann Patentanwälte
Radeckestrasse 43
D-81245 München (DE)

(54) **A water-based ink, ink jet recording method using same, and equipment using same.**

(57) **A water-based ink containing a pigment, a dispersant for dispersing the pigment, a water-soluble organic solvent, and water. The dispersant used is at least one compound selected from the groups (a) to (c): (a) a polymer having a hydrophilic part and a hydrophobic part, the polymer containing, as a monomer making up the hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β - ethylenic unsaturated carboxylic acid,**



where R is H or CH₃, m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16; (b) a polymer having a hydrophilic part and a hydrophobic part, the polymer containing, as a monomer making up the hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),

EP 0 622 429 A2



THE UNIVERSITY OF CHICAGO

THE UNIVERSITY OF CHICAGO PRESS



1. *Phragmites australis* (Cav.) Trin. ex Steud.



BACKGROUND OF THE INVENTIONField of the Invention

5 The present invention relates to a water-based ink with which recording can be made on not only coated paper, but also on non-coated paper generally used in offices and homes, i.e., so-called plain paper, at high printing density and quality. This invention further relates to an ink jet recording method using the ink, as well as equipment using the ink.

10 Description of the Related Art

An ink jet recording technique is advantageous in that less noise is generated during recording, and recording images of high resolution are obtained at a high speed by using heads with a high degree of integration. Such an ink jet recording technique employs, as a recording liquid, ink that is prepared by
 15 dissolving various water-soluble dyes in water or a mixture of water and an organic solvent. However, the use of water-soluble dyes often causes a problem in light resistance of recorded images because the water-soluble dyes are inherently poor in light resistance.

Owing to the fact that ink is water-soluble, there also occurs a problem in water resistance of recorded images. In other words, if recorded images are moistened with rain, sweat or drinking water, they are likely
 20 to blur or disappear.

Meanwhile, because of similar problems with respect to stationery usages involving such needs as ball pens employing dyes, various types of water pigment inks for stationery have been proposed with a view to solving the problems of resistance against light and water. From the standpoint of using water pigment inks, proposals for achieving dispersion stability, preventing ink from solidifying at ball points, and preventing
 25 abrasion of balls used in ball pens are discussed in, e.g., Japanese Patent Laid-Open No. 58-80368, No. 61-247774, No. 61-272278, No. 62-568, No. 62-101671, No. 62-101672, No. 1-249869, and No. 1-301760. Recently, ball pens, markers and the like using water-based pigment inks have been sold on the market. As ink jet recording ink using water pigment ink, Japanese Patent Laid-Open No. 56-147859, No. 56-147860, etc. propose ink using a particular water-soluble solvent and a high-molecular dispersant. Further, ink using
 30 both a pigment and a dye is proposed in Japanese Patent Laid-Open No. 4-57859, No. 4-57860, etc.

However, conventional water-based pigment ink has a disadvantage in that printing quality and density are remarkably deteriorated depending on the types of paper used, especially when recording is made on plain paper (such as copying paper and bond paper widely used in offices). In general, since the surface condition of plain paper is not uniform, unlike specific paper for ink jet recording, the quality of prints on
 35 plain paper varies depending on differences in absorption, spread and other properties of the ink. From the viewpoint particularly of printing density, which affects the quality of prints to a large extent, printing quality is less affected by ink using water-soluble dyes depending on the surface condition of paper as dyes are fixed to paper fibers and tend to easily stay on the paper surface. On the other hand, because water-based pigment ink establishes printing density by leaving pigments on the paper surface, the paper surface
 40 condition largely affects the printing density. More specifically, water-based pigment ink employs alkali-soluble resins as a dispersant in most cases so that printing density is increased by agglomeration of the resins on the paper surface. Although printing quality and density are remarkably deteriorated with some types of paper, it is thought that the use of alkali-soluble resins, especially (meth-) acrylic acid copolymers, is effective in not only satisfying printing quality and density, but also providing satisfactory dispersion of
 45 pigments and other properties. On the other hand, if those resins are used with ink for ink jet recording, many problems concerning reliability such as discharge stability, dispersion stability for a long term, and solidification of ink left at the fine nozzle end for a long time would be remained unsolved. This means that the use of those resins makes it difficult to achieve the desired printing density and quality and the desired reliability at the same time.

50 As means for improving printing density and quality, ink using alkali-soluble resins as a dispersant is disclosed in, e.g., Japanese Patent Laid-Open No. 56-147863, No. 56-147868, No. 56-157470, No. 60-223074 and No. 60-223075. However, the disclosed types of ink cannot provide satisfactory printing density and quality when used for ink jet recording.

Accordingly, there has been demand for an ink which can improve printing density and quality while
 55 meeting the reliability, required when used for ink jet recording, and particularly, stability in dispersion and discharge.

SUMMARY OF THE INVENTION




In view of the above-discussed problems in the prior art, an object of the present invention is to provide a water-based pigment ink with which recording can be made on various kinds of plain paper at a high printing density and quality while ensuring satisfactory reliability. Providing an ink jet recording method using the ink, as well as equipment using the ink, is also an objective.

Another object of the present invention is to provide a water-based pigment ink which has satisfactory reliability in prevention of ink from solidifying at the fine nozzle end (orifice), stability during storage for a long term, etc., and an ink jet recording method using the ink.

The above objects are achieved by the present invention as follows.



The water-based ink according to the invention that comprises a pigment, a dispersant for dispersing the pigment, a water-soluble organic solvent, and water, wherein the dispersant is at least one compound selected from the group consisting of (a) to (c):

(a) a polymer having a hydrophilic part and a hydrophobic part, the polymer containing, as a monomer making up the hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β - ethylenic unsaturated carboxylic acid,



where R is H or CH₃, m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16;

(b) a polymer having a hydrophilic part and a hydrophobic part, the polymer containing, as a monomer making up the hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),



where R₁ is H or CH₃ and R₂ is an alkyl group with 1 to 5 carbons; and

(c) polyethyleneimine.

Also, the water-based ink according to the invention contains a pigment, a dispersant, a water-soluble organic solvent, and water, wherein the ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol and dialkyl ether of triol, and white inorganic fine particles.

Further, the water-based ink according to the invention contains a pigment, a dispersant, a water-soluble organic solvent, and water, wherein the ink contains, as the water-soluble organic solvent, at least one selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol and dialkyl ether of triol, and as the dispersant, rosin-denaturated maleic acid.

The ink jet recording method according to the invention resides in that droplets of ink containing a recording agent and a liquid medium is discharged through orifices of a recording head in accordance with a recording signal to thereby make recording on a recording material, wherein the ink is any one of the above types of aqueous ink.

5 The recording unit according to the invention comprises an ink receptacle containing ink and a head portion for discharging the ink in the form of ink droplets, wherein the ink is any one of the above types of aqueous ink.

The ink cartridge according to the invention comprises an ink receptacle containing ink, wherein the ink is any one of the above types of aqueous ink.

10 The ink jet recording apparatus according to the invention includes a recording unit comprising an ink receptacle containing ink and a head portion for discharging the ink in the form of ink droplets, wherein the ink is any one of the above types of aqueous ink.

The ink jet recording apparatus according to the invention comprises a recording head for discharging ink droplets, an ink cartridge having an ink receptacle containing ink, and an ink supply portion for
15 supplying the ink from the ink cartridge to the recording head, wherein the ink is any one of the above types of aqueous ink.

BRIEF DESCRIPTION OF THE DRAWINGS

20 Fig. 1(a) is a sectional view of one example of the structure of a head according to the present invention.

Fig. 1(b) is a sectional view of a cross-section taken along line 1(b)-1(b) in Fig. 1(a).

Fig. 2 is a perspective view of a multi-head comprising a number of heads, shown in Fig. 1(a), arranged side by side.

25 Fig. 3 is a perspective view of an ink jet recording apparatus in which the head of the present invention is incorporated.

Fig. 4 is a sectional view of one example of an ink cartridge which contains ink supplied to the head through an ink supply tube.

Fig. 5 is a perspective view of one example of an ink jet recording apparatus in which the head and the
30 ink cartridge are integral with each other.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

As a result of intensively studying the causes of deteriorating printing quality and density depending on
35 the types of paper used when ink jet recording is performed on plain paper with ink using water-based pigments, the inventors have discovered that the surface condition of paper largely affects printing quality, especially printing density. In other words, water-based pigment ink establishes printing density owing to the fact that discharged ink starts agglomerating immediately after reaching the paper surface and then remains there. If the paper has such a surface condition as to cause the ink to lose stability, good printing
40 density is obtained, but if the ink starts to penetrate before agglomerating, the desired printing density cannot be obtained. While plain paper is mainly classified into acid paper and neutralized paper, any kind of paper can be subjected to various treatments depending on applications, and hence has different surface conditions. This results in difficulties in designing an ink so that the ink begins to instantaneously agglomerate on the paper surfaces under every condition. Further, designing an ink so that it is unstable in
45 a dispersion state, providing desired printing density, as described above, is contradictory to the reliability required for ink jet recording ink, i.e., discharge stability, stability during storage for a long term, and prevention of solidification of ink left for a long time at the fine nozzle end (orifice).

With attention focused on a dispersant for use with water-based pigment inks, the inventors have found that, by using at least one polymer selected from the above groups (a) to (c) as a dispersant, desired
50 printing density and quality can be obtained simultaneously with achievement of satisfactory reliability required for ink jet recording ink, i.e., discharge stability, stability during storage for a long term, and prevention of ink left for a long time from solidifying at the fine nozzle end of an ink jet recording apparatus.

The inventors have also found that printing density and discharge characteristics are improved by using a combination of pigments and white inorganic fine particles, and a specific solvent, or by using rosin-
55 denaturated maleic acid, as a dispersant, and a particular solvent in combination.

The present invention will hereinafter be described in detail.

The water-soluble resin selected from the above group (a) and used as a dispersant in the present invention contains 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is

selected from the above three types of compounds having the general structures represented by the formulae (I) to (III). Examples of such a monomer include:

as for the formula (I), $\text{CH}_2 = \text{C(R)} - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_m\text{H}$ ($m = 2$ to 24);

$\text{CH}_2 = \text{C}(\text{CH}_3) - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_m\text{H}$: Blenmer-PE-90 ($m = 1.9$, Nippon Oil & Fats, Co.),

$\text{CH}_2 = \text{C}(\text{CH}_3) - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_m\text{H}$: Blenmer-PE-200 ($m = 4.4$, Nippon Oil & Fats, Co.),

$\text{CH}_2 = \text{C}(\text{CH}_3) - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_m\text{H}$: Blenmer-PE-350 ($m = 7.7$, Nippon Oil & Fats, Co.), and

$\text{CH}_2 = \text{CH} - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_m\text{H}$ ($m = 24$): on experimental basis;

as for the formula (II), $\text{CH}_2 = \text{C(R)} - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_n - (\text{CH}_2)_l\text{H}$ ($n = 2$ to 24 , $l = 1$ to 12);

methoxytriethylene glycol acrylate ($\text{R} = \text{H}$, $n = 3$, $l = 1$): NK ester AM-30G,

methoxypolyethylene glycol #400 acrylate ($\text{R} = \text{H}$, $n =$ approximately 10 , $l = 1$): NK ester AM-90G,

methoxydiethylene glycol methacrylate ($\text{R} = \text{CH}_3$, $n = 2$, $l = 1$): NK ester M-20G,

methoxytetraethylene glycol methacrylate ($\text{R} = \text{CH}_3$, $n = 4$, $l = 1$): NK ester M-40G,

methoxypolyethylene glycol #400 methacrylate ($\text{R} = \text{CH}_3$, $n =$ approximately 10 , $l = 1$): NK ester M-90G,

methoxypolyethylene glycol #1000 methacrylate ($\text{R} = \text{H}$, $n = 3$, $l = 1$): NK ester AM-230G, and

butoxydiethylene glycol acrylate ($\text{R} = \text{H}$, $n = 2$, $l = 4$): NK ester AB-20G (all these products being manufactured by Shin Nakamura Chemical Industry Co., Ltd.); and

as for the formula (III), $\text{CH}_2 = \text{C(R)} - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_p - \text{phenyl} - (\text{CH}_2)_q\text{H}$ ($p = 1$ to 12 , $q = 0$ to 16);

phenoxydiethylene glycol acrylate ($\text{R} = \text{H}$, $p = 2$, $q = 0$): NK ester AMP-20G,

phenoxytriethylene glycol acrylate ($\text{R} = \text{H}$, $p =$ approximately 5 , $q = 0$): NK ester AMP-60G,

nonylphenoxyethyl acrylate ($\text{R} = \text{H}$, $p = 1$, $q = 8$): NK ester NPA-10G (all these products being manufactured by Shin Nakamura Chemical Industry Co., Ltd.), and

$\text{CH}_2 = \text{CH} - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_{10} - \text{phenyl} - (\text{CH}_2)_{16}\text{H}$: on experimental basis.

Further, it is essential for the present ink to contain, as a hydrophilic monomer, 5 to 60 mol% of α , β -ethylenic unsaturated carboxylic acid. Examples of such a monomer include acrylic acid, methacrylic acid, maleic acid, itaconic acid, fumaric acid, etc. Derivatives of these acids may also be used.

Examples of a hydrophobic monomer for use in copolymerization of the dispersant in the present invention include styrenes such as styrene, α -methylstyrene and vinyltoluene, and (meth-)acryl acid alkyl esters. The (meth-)acryl acid alkyl esters includes methyl (meth-)acrylate, ethyl (meth-)acrylate, propyl (meth-)acrylate, isopropyl (meth-)acrylate, *n*-butyl (meth-)acrylate, *sec*-butyl (meth-)acrylate, *tert*-butyl (meth-)acrylate, 2-methylbutyl (meth-)acrylate, 2-ethylbutyl (meth-)acrylate, 3-methylbutyl (meth-)acrylate, 1,3-dimethylbutyl (meth-)acrylate, pentyl (meth-)acrylate, 3-pentyl (meth-)acrylate, hexyl (meth-)acrylate, 2-ethyl hexyl (meth-)acrylate, heptyl (meth-)acrylate, octyl (meth-)acrylate, nonyl (meth-)acrylate, 2-ethoxyethyl acrylate, 3-ethoxypropyl acrylate, 2-ethoxybutyl acrylate, 3-ethoxybutyl acrylate, and dimethylaminoethyl acrylate. An alcohol ingredient for use in half-esterification includes methanol, ethanol, and propanol.

Polymerization of the dispersant in the present invention using such monomers can readily be performed by radical copolymerization.

The weight-average molecular weight of the polymer is preferably in the range of 500 to 30000, more preferably 1000 to 15000.

Further, the content of the polymer is preferably in the range of 0.1 to 5 wt% with respect to the total ink weight.

It has been confirmed that the use of the polymer described above is highly effective in not only improving printing density and quality due to an agglomerating effect provided by the α , β -ethylenic unsaturated carboxylic acid, but also in ensuring discharge stability, stability during storage for a long term, and prevention of ink left for a long time from solidifying at the fine nozzle end which are required for ink jet recording ink, due to an effect of the long-chain nonionic group containing monomer, i.e., an improvement in solubility and pH-stability. Additionally, it has also been confirmed that mixing the long-chain nonionic group containing monomer in the dispersant is also effective in improving printing density and quality.

The water-soluble resin selected from the above group (b) and used as a dispersant in the present invention contains in a copolymer, a monomer having a hydrophobic part, 5 to 70 mol% of at least one monomer having the general structure represented by the formula (IV) or (V). Practically, examples of such a monomer include vinyl acetate, isopropenyl acetate, allyl acetate, allyl propionate, vinyl butyrate, allyl butyrate, etc.

Other hydrophobic monomers for use in copolymerization include styrene, styrene derivatives, vinyl-naphthalene, vinyl-naphthalene derivatives, etc.

Examples of a hydrophilic monomer for use in copolymerization include acrylic acid, acrylic acid derivatives, maleic acid, maleic acid derivatives, itaconic acid, itaconic acid derivatives, fumaric acid, fumaric acid derivatives, etc.

- 5 Polymerization of the dispersant in the present invention using such monomers can readily be performed by radical copolymerization.

The weight-average molecular weight of the polymer is preferably in the range of 500 to 30000, more preferably 1000 to 15000.

Further, the content of the copolymer is preferably in the range of 0.1 to 5 wt% with respect to the total ink weight.

- 10 The water-soluble resin given by the above group (c) and used as a dispersant in the ink of the present invention is polyethyleneimine. This polymer is not a completely linear high molecular weight molecule, but has branched parts to some extent and includes primary, secondary and tertiary amino nitrogen. Properly an ion- or cation-denaturated polyethyleneimine can also satisfactorily be used. Practical examples include Epomin series manufactured by Nippon Shokubai Co., Ltd. The weight-average molecular weight of the polymer is preferably in the range of 1000 to 40000. Further, the content of the polymer is preferably in the range of 0.1 to 10 wt% with respect to the total ink weight.

- 15 Since polyethyleneimine itself has higher pH-stability and resolubility than alkali-soluble resins conventionally used as a dispersant, its use is thought to be very effective in ensuring discharge stability, stability during storage for a long term, and prevention of ink left for a long time from solidifying at the fine nozzle end, which are required for ink jet recording ink. Conversely, it is generally inferred that the use of polyethyleneimine having such properties deteriorates printing density and quality, as described above. The satisfactory printing density and quality resulted herein are presumably based on the fact that polyethyleneimine itself has high affinity with the paper component, but the genuine reason is not yet clear.

- 20 Further, the inventors have found that wiping resistance of prints is improved in the case of using polyethyleneimine.

- 25 The content of pigment in the ink of the present invention, which contains at least one polymer selected from the above groups (a) to (c), is preferably in the range of 1 to 20 wt%, more preferably 2 to 12 wt%, for the total ink weight. So long as the above condition is satisfied, any desired pigment can be used in the present invention. As carbon black for use in black ink, there can be used one which is manufactured by the furnace method or the channel method, and has the primary particle size of 15 to 40 nm, a specific surface area of 50 to 300 m²/g according to the BET method, a DBP oil absorption amount of 40 to 150 ml/100 g, a volatile ingredient of 0.5 to 10 %, and a pH value of 2 to 9, e.g., such as, for example, commercially available carbon black NO. 2300, NO. 900, MCF88, NO. 33, NO. 40, NO. 45, NO. 52, MA7, MA8 and NO. 2200B (by Mitsubishi Chemical Industries Co., Ltd.), RAVEN 1255 (by Columbia Co.), MOGUL L (by Cabot Co.), and Color Black FW1, Color Black FW18, Color Black S170, Color Black S150 and Printex U (by Degussa, AG). Other carbon black newly manufactured for the present invention can also be used.
- 35 Examples of a pigment for use in yellow ink include C.I. Pigment Yellow 1, C.I. Pigment Yellow 2, C.I. Pigment Yellow 3, C.I. Pigment Yellow 13, C.I. Pigment Yellow 16, and C.I. Pigment Yellow 83. Examples of a pigment for use in magenta ink include C.I. Pigment Red 5, C.I. Pigment Red 7, C.I. Pigment Red 12, C.I. Pigment Red 48(Ca), C.I. Pigment Red 48(Mn), C.I. Pigment Red 57(Ca), C.I. Pigment Red 112, and C.I. Pigment Red 122. Examples of a pigment for use in cyan ink include C.I. Pigment Blue 1, C.I. Pigment Blue 2, C.I. Pigment Blue 3, C.I. Pigment Blue 15:3, C.I. Pigment Blue 16, C.I. Pigment Blue 22, C.I. Vat Blue 4, and C.I. Vat Blue 6. In addition, other pigments newly manufactured for the present invention can also be used.

- 40 Moreover, the ink of the present invention is preferably prepared to be neutral or alkaline as a whole for the purpose of improving solubility of the above-described water-soluble resin and ensuring higher stability during storage for a long term. In this connection, however, since various members used in the ink jet recording apparatus may be apt to corrode, the pH range is preferably held in the range of 7 to 10.

- 45 Examples of a pH adjuster include various organic amines such as diethanolamine and triethanolamine, inorganic alkaline agents such as hydroxides of alkaline metals including sodium hydroxide, lithium hydroxide, potassium hydroxide, etc., organic acids, and mineral acids.

The above-described pigment and water-soluble resin are dispersed or dissolved in a water-based medium.

- 50 A water-based medium suitable for the ink of the present invention is a mixture of water and a water-soluble solvent. Preferably used as the water is not usual water containing various ions, but ion-exchanged water (deionized water).

As other optional solvent ingredient which can be used in combination with the above-described ingredients, a water-soluble organic solvent to be mixed to water includes, for example, alkyl alcohols with 1

to 4 carbons such as methyl alcohol, ethyl alcohol, n-propyl alcohol, isopropyl alcohol, n-butyl alcohol, sec-butyl alcohol, and tert-butyl alcohol; amides such as dimethyl formamide and dimethyl acetoamide; ketones or ketone alcohols such as acetone and diacetone alcohol; ethers such as tetrahydrofuran and dioxane; polyalkylene glycols such as polyethylene glycol and polypropylene glycol; alkylene glycols with alkylene groups each containing 2 to 6 carbons, such as ethylene glycol, propylene glycol, butylene glycol, triethylene glycol, 1, 2, 6-hexanetriol, thiodiglycol, hexylene glycol, and diethylene glycol; glycerin; lower alkyl ethers of polyhydric alcohols, such as monomethyl(or ethyl) ether of ethylene glycol, methyl (or ethyl) ether of diethylene glycol, and monomethyl (or ethyl) ether of triethylene glycol; N-methyl-2-pyrrolidone, 2-pyrrolidone, and 1,3-dimethyl-2-imidazolidinone. Of these many water-soluble organic solvents, polyhydric alcohols such as diethylene glycol and lower alkyl ethers of polyhydric alcohols, such as monomethyl(or ethyl) ether of triethylene glycol, are preferable.

To provide discharge stability, it is effective to add ethanol, isopropyl alcohol, or lower alkyl ethers of polyhydric alcohols. It is believed that air bubbles can more steadily be generated in the ink over a thin-film resistor by addition of such a solvent.

A water-soluble solvent especially preferably combined with the dispersant (a) includes monoalkyl ether of diol and/or monoalkyl ether of triol and/or dialkyl ether of triol (with an alkyl group having 4 or more carbons). Among them, monobutyl ether of diethylene glycol, monobutyl ether of ethylene glycol, monobutyl ether of triethylene glycol, monopentyl ether of glycerin, dihexyl ether of 1,2,6-hexane-triol, diethyl ether of 1,2,4-butanetriol, etc. The content of monoalkyl ether of diol and/or monoalkyl ether of triol and/or dialkyl ether of triol (with an alkyl group having 4 or more carbons) is preferably in the range of 0.01 to 5 wt% for the total ink weight from the standpoint of improving printing density, printing quality and deposit of the ink.

The content of the water-soluble organic solvent in the ink of the present invention is usually in the range of 3 to 50 wt%, preferably 3 to 40 wt%, for the total ink weight. The content of the water used is in the range of 10 to 90 wt%, preferably 30 to 80 wt%, for the total ink weight.

In order for the ink to have further desired physical properties, a surfactant, a bubble retarder, an antiseptic, etc. can be added to the ink of the present invention, if necessary, in addition to the above-described ingredients. Commercially available water-soluble dyes can also be added.

So long as stability during storage and other required properties of the ink will not adversely be affected, no limitations exist on the kind of surfactant used. There are, e.g., anionic surfactants such as fatty acid salts, ester sulfates of higher alcohols, ester sulfates of liquid fatty oil, and alkylallyl sulfonates; and nonionic surfactants such as polyoxyethylene alkyl ethers, polyoxyethylene alkyl esters, polyoxyethylenesorbitane alkyl esters, acetylene alcohol, and acetylene glycol. One or two surfactants properly selected from the above examples can be used. Depending on the kind of dispersant, the amount of surfactant(s) used is preferably in the range of 0.01 to 5 wt% for the total ink weight. In this connection, the surfactant content is preferably selected so that the ink has a surface tension not less than 30 dyne/cm. The reason is that if the surface tension of the ink is less than the above value, problems trouble such as printing deviation (i.e., shift in arrival point of the ink droplet) would be caused due to wetting at the nozzle end in the ink jet recording intended by the present invention.

A second aspect of the present invention resides in water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein the ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol and dialkyl ether of triol, and white inorganic fine particles.

The white inorganic particles for use with the second aspect of the present invention are preferably titanium dioxide fine particles or alumina fine particles, but are not limited thereto. Any other fine particles may also be used so long as they can stably disperse together with the pigment used as a color material in the ink jet recording ink. While no special limitations exist on the particle shape, spherical particles are preferably used. Further, these particles may be surface-treated to become hydrophilic or hydrophobic. Among them, titanium dioxide particles whose surfaces are treated to be hydrophilic are especially preferable. These types of particles are on the market as, for example, the Titania series from Idemitsu Kosan Co., Ltd. Other types of titanium dioxide fine particles or alumina fine particles are on the market as, e.g., Titanium Dioxide P25 and Aluminum Oxide C from Nippon Aerosil Co., Ltd.

The ratio of primary particle size of the white inorganic fine particles contained in the ink to primary particle size of the pigment contained together as a color material is preferably in the range of 1/10 to 5/1. If the ratio is out of that range, it would be hard to achieve the optimum effect of the present invention, particularly with respect to a satisfactory result in printing quality and density. Considering the particle size of the pigment for use in the ink jet recording ink, the primary particle size of the white inorganic fine particles is in the range of 5 to 200 nm, but the range of 5 to 100 nm is preferable for sufficiently fulfilling

the objects of the present invention. The content ratio in weight of the white inorganic fine particles to the pigment used together as a color material is preferably in the range of 1/20 to 1/1. If the content ratio in weight is less than 1/20, it would be hard to achieve the optimum good result in printing quality and density. If the content ratio in weight is larger than 1/1, it would be hard to achieve the optimum good result in reliability such as discharge stability and stability during storage. The range of 1/10 to 1/2 is more preferable for optimally fulfilling the objects of the present invention.

While any type of water-soluble resin can be used as a dispersant for the pigment, as a color material, and white inorganic fine particles for use with the second aspect of the present invention, its weight-average molecular weight is preferably in the range of 500 to 30000, more preferably 1000 to 15000. Practical examples of the water-soluble resin include block copolymers or random copolymers, or salts thereof, these copolymers each consisting of two or more monomers selected from styrene, styrene derivatives, vinyl-naphthalene, vinyl-naphthalene derivatives, aliphatic alcohol esters of α , β - ethylenic unsaturated carboxylic acid, acrylic acid, acrylic acid derivatives, maleic acid, maleic acid derivatives, itaconic acid, itaconic acid derivatives, fumaric acid, fumaric acid derivatives, etc. These resins are particularly preferably used in ink jet recording ink, because they are alkali-soluble resins which are soluble in an aqueous solution containing a base dissolved therein and hence have advantages of enabling lower viscosity of the disperse solution and easier dispersion. Alternatively, a homopolymer of a hydrophilic monomer or salt thereof may be used. Other water-soluble resins such as polyvinyl pyrrolidone, polyvinyl alcohol, carboxymethyl cellulose, and a condensation product of naphthalene sulfonate - formaldehyde, and natural resins such as rosin and shellac can also be used. In addition, various surfactants such as polyoxyethylene alkyl ethers and polyoxyethylene alkyl esters may be used. The content of the water-soluble resin and the surfactant is preferably in the range of 0.1 to 5 wt% for the total ink weight. The above-described pigment, white inorganic fine particles and water-soluble resin are dispersed or dissolved in the water-based medium.

A third aspect of the present invention resides in a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein the ink contains, as the water-soluble organic solvent, at least one selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol and dialkyl ether of triol, and as the dispersant, rosin-denaturated maleic acid.

The rosin-denaturated maleic acid for use with the third aspect of the present invention has no limitations on the kind thereof, and its commercially available products include Malkyd No. 31 and Malkyd No. 32 (by Arakawa Chemicals Co., Ltd), Hiparac C and Hiparac PR (by Nippon Shellac Co., Ltd.), Harimac 145P and Harimac R-120AH (by Harima Chemical Industry Co., Ltd.), etc. While any type water-soluble resin can be used as a dispersant in combination with the above ingredients in the present invention, its weight-average molecular weight is preferably in the range of 500 to 30000, more preferably 1000 to 15000. Practical examples of the water-soluble resin include block copolymers or random copolymers, or salts thereof, these copolymers each consisting of two or more monomers selected from styrene, styrene derivatives, vinyl-naphthalene, vinyl-naphthalene derivatives, aliphatic alcohol esters of α , β - ethylenic unsaturated carboxylic acid, acrylic acid, acrylic acid derivatives, maleic acid, maleic acid derivatives, itaconic acid, itaconic acid derivatives, fumaric acid, fumaric acid derivatives, etc. These resins are particularly preferably used in ink jet recording ink, because they are alkali-soluble resins which are soluble in an aqueous solution containing a base dissolved therein and hence have advantages of enabling lower viscosity of the disperse solution and easier dispersion. Alternatively, a homopolymer of a hydrophilic monomer or salt thereof may be used. Other water-soluble resins such as polyvinyl pyrrolidone, polyvinyl alcohol, carboxymethyl cellulose, and a condensation product of naphthalene sulfonate - formaldehyde; and natural resins, e.g., shellac can also be used. In addition, various surfactants such as polyoxyethylene alkyl ethers and polyoxyethylene alkyl esters may be used. The content of the water-soluble resin and the surfactant is preferably in the range of 0.1 to 5 wt% for the total ink weight.

The ink according to any of the aspects of the present invention described above is prepared by adding a pigment to an aqueous solution containing at least a dispersion resin and water, agitating and then dispersing the mixed solution by using dispersion means (described later), and carrying out a process of centrifugal separation, if necessary, thereby obtaining a desired disperse solution. After that, the other ingredients described above are added to the disperse solution and agitated to produce the ink.

Before the solution containing the pigment is subjected to the dispersion process, it is also required to carry out pre-mixing for 30 minutes or more. This pre-mixing operation serves to improve wetting of the pigment surface and to promote adsorption onto the pigment surface.

Bases to be added to the disperse solution in the case of using an alkali-soluble resin are preferably organic amines such as monoethanolamine, diethanolamine, triethanolamine, amine methylpropanol and ammonia, or inorganic bases such as potassium hydroxide and sodium hydroxide.

On the other hand, any types of dispersers which are usually employed can be used in the present invention, and include, e.g., a ball mill, a roll mill and a sand mill.

Among them, a high-speed sand mill is preferable and is commercially available as, e.g., Super Mill, Sand Grinder, Beads Mill, Agitator Mill, Grain Mill, Dyno Mill, Pearl Mill and Cobol Mill (all trade names).

For obtaining a disperse system of the pigment having the desired grain size distribution, the present invention employs a method of reducing the size of pulverizing media in a disperser, increasing the loading rate of the pulverizing media, prolonging the process time, slowing the discharge speed, or sorting the resultant grains through a filter or centrifugal separator after the pulverization. Any combinations of those methods can also be used.

A recording apparatus suitable to make recording with the ink of the present invention is arranged such that the ink in a chamber defined within a recording head is supplied with thermal energy corresponding to a recording signal, and an ink droplet is produced by the supplied energy.

One example of the structure of the head, as a primary part, is shown in Figs. 1(a), 1(b) and 2. A head 13 is constructed by bonding a glass, ceramic or plastic plate having a channel 14 through which ink is passed, and a heat generating head 15 for use in heat-sensitive recording (the figure showing a thin film head only by way of example) with each other. The heat generating head 15 comprises a protective film 16 formed of, e.g., silicon oxide, aluminum electrodes 17-1, 17-2, a heat-generating resistance material layer 18 formed of, e.g., Nichrome, a heat accumulating layer 19, and a base plate 20 formed of, e.g., alumina and having a high heat radiating ability.

Ink 21 is filled to reach a discharge orifice (fine hole) 22 and forms a meniscus 23 under a pressure P.

When an electric signal is applied to the electrodes 17-1 and 17-2, a region of the heat generating head 15 indicated by n abruptly generates heat so that an air bubble is produced in the ink 21 contacting the region n. The meniscus 23 is projected forwardly with a resultant pressure, causing the ink 21 to discharge and fly in the form of recording droplets 24 from the orifice 22 toward a material 25 on which recording is to be made. Fig. 2 shows an appearance of a multi-head comprising a number of heads, shown in Fig. 1(a), arranged side by side. The multi-head is constructed by bonding a glass plate 27 formed with multiple channels 26 and a heat generating head 28 similar to that described above by referring to Fig. 1(a) with each other.

Incidentally, Fig. 1(a) is a sectional view of the head taken along an ink flow passage, and Fig. 1(b) is a sectional view taken along line 1(b)-1(b) in Fig. 1(a).

Fig. 3 shows one example of an ink jet recording apparatus in which the above-described head is incorporated. In Fig. 3, denoted by 61 is a blade as a wiping member in the form of a cantilever, of which one end is held by a blade holding member to become a fixed end. The blade 61 is disposed at a position adjacent a recording area covered by the recording head and, in the illustrated embodiment, it is held in such a manner as to project into the travel path of the recording head. 62 is a cap which is disposed at its home position adjacent the blade 61 and is movable in a direction perpendicular to the direction of movement of the recording head such that it comes into contact with the ink discharge surface for capping the same. 63 is an ink absorber which is disposed adjacent the blade 61 and is held in such a manner as to project into the travel path of the recording head similarly to the blade 61. The blade 61, the cap 62 and the absorber 63 cooperatively construct a discharge recovery unit 64 in which the blade 61 and the absorber 63 serve to remove moisture, dust, dirt, etc. on the ink discharge surface. 65 is a recording head which includes discharge energy generating means and discharges ink onto a material, on which recording is to be made and which is disposed facing the ink discharge surface including discharge ports arrayed therein, for thereby recording an image. 66 is a carriage on which the recording head 65 is mounted to be reciprocally moved. The carriage 66 is slidably engaged with a guide shaft 67 and is also connected (though not shown) at its part to a belt 69 driven by a motor 68. With such an arrangement, the carriage 66 is movable along the guide shaft 67 so that the recording head 65 can move over the recording area and an area adjacent thereto.

Denoted by 51 is a paper feeding portion through which the recording material is inserted, and 52 is a paper feeding roller driven by a motor (not shown). With such an arrangement, the recording material is fed to a position facing the ink discharge surface of the recording head, and is then guided to a paper discharging portion including paper discharging rolls 53 with the progress of recording.

In the above arrangement, when the recording head 65 is returned to the home position upon the end of recording or other reason, the cap 62 of the head recovery unit 64 is retracted from the travel path of the recording head 65, but the blade 61 is held projected into the travel path. As a result, the ink discharge surface of the recording head 65 is wiped by the recording head 65. When the cap 62 is brought into contact with the ink discharge surface of the recording head 65 for capping the same, it is moved to project into the travel path of the recording head.

When the recording head 65 is moved from the home position to the recording start position, the cap 62 and the blade 61 are in the same positions as those during the above wiping. In that movement, therefore, the ink discharge surface of the recording head 65 is similarly wiped.

The movement of the recording head to the home position adjacent the recording area is performed not only upon the end of recording or the recovery of discharge, but also at predetermined intervals during the time in which the recording head is reciprocally moved over the recording area for recording an image. For each of such movements, the wiping of the ink discharge surface of the recording head is made.

Fig. 4 shows one example of an ink cartridge 45 containing ink supplied to the head through an ink supply tube. In Fig. 4, 40 is an ink bag which contains the ink to be supplied and has a rubber-made plug 42 provided at its distal end. By inserting a needle (not shown) through the plug 42, the ink in the ink bag 40 can be supplied to the head. 44 is an ink absorber for accommodating waste ink.

The ink jet recording apparatus for use in the present invention is not limited to the above-described construction in which the head and the ink cartridge are separate from each other, and can also suitably be applied to the construction in which both the members are integral with each other as shown in Fig. 5.

Referring to Fig. 5, 70 is an ink jet cartridge in which an ink absorber impregnated with ink is housed. The ink existing in the ink absorber is discharged in the form of ink droplets through a head portion 71 having a plurality of orifices. 72 is an atmosphere communicating port via which the interior of the cartridge is communicated with the atmosphere.

The ink jet cartridge 70 is used in place of the recording head 65 shown in Fig. 3 and is detachably attached to the carriage 66.

Examples

Examples using a polymer selected from the group (a) as dispersant

Example 1

(Polymerization Example 1)

50 mol% of styrene, 35 mol% of acrylic acid, and 15 mol% of Blemmer-PE-200 were each put in a mixed solvent of ethylene glycol - monomethyl ether and isopropyl alcohol, and then subjected to solution polymerization in accordance with the ordinary process. Thereby, a polymer 1 for use in the present invention with number-average molecular weight of 9700 and weight-average molecular weight of 13500 was obtained.

(Preparation of Pigment Dispersed Solution)

polymer 1 polymerized above	3 parts
monoethanolamine	1 part
ion-exchanged water	75 parts
diethylene glycol	5 parts

The above ingredients were mixed and heated to 50 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 15 parts of new experimentally manufactured carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd.) and 1 part of isopropyl alcohol, followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the conditions below:

dispersion machine; Sand Grinder (Igarashi Machine Co., Ltd.)
 pulverizing media; zirconium beads of 1 mm diameter
 charging rate of pulverizing media; 50 % (volume)
 pulverizing time; 3 hours

The centrifugal separation process (12000 RPM, 20 minutes) was further carried out to remove coarse particles, then by preparing a disperse solution.

(Preparation of Ink)

above disperse solution	30 parts
glycerol	2 parts
diethylene glycol	15 parts
N-methyl pyrrolidone	4 parts
isopropyl alcohol	3 parts
ion-exchanged water	46 parts

For the ink thus prepared, later-described evaluations were conducted by using an ink jet recording apparatus BJ-10V (trade name, by Canon Inc.) with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Example 2

(Polymerization Example 2)

45 mol% of α - methylstyrene, 45 mol% of methacrylic acid, and 10 mol% of methoxytetraethylene glycol methacrylate (NK ester M-40G) were each put in a mixed solvent of ethylene glycol - monomethyl ether and isopropyl alcohol, and then subjected to solution polymerization in accordance with the ordinary process. Thereby, a polymer 2 for use in the present invention with a number-average molecular weight of 4900 and a weight-average molecular weight of 8800 was obtained.

(Preparation of Pigment Dispersed Solution)

polymer 2 polymerized above	3.5 parts
aminomethyl propanol	0.5 part
ion-exchanged water	78 parts
diethylene glycol	5 parts

The above ingredients were mixed and heated to 50 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution was 13 parts of carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd.), followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the conditions below:

dispersion machine; Pearl Mill (Ashizawa Co., Ltd.)
 pulverizing media; glass beads of 1 mm diameter
 charging rate of pulverizing media; 50 % (volume)
 delivery rate; 100 ml/minute

The centrifugal separation process (12000 RPM, 20 minutes) was further carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

above disperse solution	25 parts
glycerol	8 parts
ethylene glycol	5 parts
ethanol	5 parts
Emulgen 920 (by Kao Co., Ltd.)	0.1 part
ion-exchanged water	56.9 parts

For the ink thus prepared, later-described evaluations were conducted using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy

corresponding to a recording signal.

Example 3

5 (Polymerization Example 3)

52 mol% of methyl methacrylate, 8 mol% of phenoxy polyethylene glycol acrylate (NK ester AMP-60G), and 40 mol% of acrylic acid were each put in a mixed solvent of ethylene glycol - monomethyl ether and butyl alcohol, and then subjected to solution polymerization in accordance with the ordinary process.
10 Thereby, a polymer 3 for use in the present invention with a number-average molecular weight of 7600 and a weight-average molecular weight of 12500 was obtained.

(Preparation of Pigment Dispersed Solution)

15

polymer 3 polymerized above	1.5 parts
ion-exchanged water	77.5 parts
ethylene glycol	5 parts

20

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 15 parts of new experimentally manufactured carbon black (S170 by Degussa AG) and 1 part of isopropyl alcohol, followed by pre-mixing for 60 minutes. After that, the dispersion process was carried out under the conditions below:

25 dispersion machine; Sand Grinder (Igarashi Machine Co., Ltd.)

pulverizing media; zirconium beads of 0.5 mm diameter

charging rate of pulverizing media; 70 % (volume)

pulverizing time; 10 hours

The centrifugal separation process (12000 RPM, 20 minutes) was further carried out to remove coarse
30 particles, thereby preparing a disperse solution.

(Preparation of Ink)

35

above disperse solution	30 parts
glycerol	12 parts
diethylene glycol	15 parts
2-pyrrolidone	5 parts
isopropyl alcohol	3 parts
40 Surfynol 61 (by Kawaken Fine Chemical Co., Ltd.)	0.1 part
ion-exchanged water	34.9 parts

40

For the ink thus prepared, later-described evaluations were conducted using the ink jet recording apparatus
45 with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Example 4

50 (Polymerization Example 4)

55 55 mol% of α - methylstyrene, 35 mol% of acrylic acid, and 10 mol% of an experimentally manufactured monomer $\text{CH}_2 = \text{CH} - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_{24}\text{H}$ were each put in a mixed solvent of ethylene glycol - monomethyl ether and isopropyl alcohol, and then subjected to solution polymerization in accordance with the ordinary process. Thereby, a polymer 4 for use in the present invention with a number-average molecular weight of 6800 and a weight-average molecular weight of 10200 was obtained.

(Preparation of Pigment Dispersed Solution and Ink)

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as Example 1 except that the dispersion resin was replaced by the polymer 4 polymerized above in the preparation of both the pigment dispersed solution and the ink in Example 1.

Example 5

(Polymerization Example 5)

48 mol% of styrene, 45 mol% of methacrylic acid, and 7 mol% of an experimentally manufactured monomer $\text{CH}_2 = \text{CH} - \text{COO} - (\text{CH}_2\text{CH}_2\text{O})_{10} - \text{phenyl} - (\text{CH}_2)_{16}\text{H}$ were each put in a mixed solvent of ethylene glycol - monomethyl ether and isopropyl alcohol, and then subjected to solution polymerization in accordance with the ordinary process. Thereby, a polymer 5 for use in the present invention with a number-average molecular weight of 6400 and a weight-average molecular weight of 9200 was obtained.

(Preparation of Pigment Dispersed Solution and Ink)

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as Example 2 except that the dispersion resin was replaced by the polymer 5 polymerized above in the preparation of both the pigment dispersed solution and the ink in Example 2.

Comparative Example 1

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as Example 1 except that the dispersion resin was replaced by a styrene - acrylic acid - butyl acrylate random copolymer (manufactured on experimental basis, acid value 135, weight-average molecular weight 5500) in Example 1.

Comparative Example 2

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as Example 2 except that the dispersion resin was replaced by a styrene - maleic acid random copolymer SMA Resin 1440 (trade name, by ARCO Chem. Co., acid value 175, weight-average molecular weight 2500) in Example 2.

Comparative Example 3

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as Example 3 except that the dispersion resin was replaced by condensed sodium naphthalene sulfonate Roma D (trade name, by Sunnopus Co., weight-average molecular weight 1800) in Example 3.

Evaluation 1

Printing density of prints

Printing was made on copying paper of Xerox 4024 and Canon NP-DRY by using the above-described ink jet recording apparatus, and printing density of the prints was measured by Macbeth densitometer (TR918).

Evaluation 2

Printing was continuously made by using the above-described ink jet recording apparatus to check at which number sheet non-discharge of the ink occurred.

Evaluation 3

Stability during storage of ink

- 5 The above-prepared aqueous ink was enclosed in a glass container and stored at 60 °C for six months. The ink which caused problems such as agglomeration of pigment particles and increase in viscosity after the storage period was marked X, and the ink which caused no problems was marked O. The evaluation results are listed in Table 1 below.

Table 1

	Evaluation Results		
	Evaluation 1 Printing Density		Evaluation 2 Number of sheets at non-discharge
	Xerox4024	NP-DRY	Evaluation 3 Stability during storage
Example 1	1.31	1.45	no occurrence for 500 sheets
Example 2	1.29	1.42	no occurrence for 500 sheets
Example 3	1.35	1.48	no occurrence for 500 sheets
Example 4	1.31	1.44	no occurrence for 500 sheets
Example 5	1.33	1.43	no occurrence for 500 sheets
Com. Ex.1	1.1	1.32	no occurrence for 500 sheets
Com. Ex.2	1.09	1.29	200 sheets
Com. Ex.3	0.98	1.24	150 sheets

- 30 As described hereinabove, the ink of the present invention has advantages, when applied to an ink jet printer utilizing thermal energy, that printed images have good durability, the ink can always be stably discharged for a long period of time even under variations in driving conditions, and satisfactory printing quality and density are obtained on any types of plain paper while ensuring high reliability and stability during long-term storage.

Example 6

- 40 Ink was prepared in the same manner as in Example 1 except that the ink ingredients in Example 1 were replaced by the following ones.

(Preparation of Ink)

45	disperse solution used in Example 1	30 parts
	diethylene glycol - monobutyl ether	0.5 part
	glycerol	2 parts
	diethylene glycol	15 parts
	N-methylpyrrolidone	4 parts
50	ion-exchanged water	48.5 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with monoethanolamine, thereby obtaining the ink of the present invention.

Example 7

Ink was prepared in the same manner as in Example 2 except that the ink ingredients in Example 2 were replaced by the following ones.

(Preparation of Ink)

disperse solution used in Example 2	25 parts
ethylene glycol - monobutyl ether	1 part
glycerol	8 parts
ethylene glycol	5 parts
ion-exchanged water	61 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with aminomethyl propanol, thereby obtaining the ink of the present invention.

Example 8

Ink was prepared in the same manner as in Example 3 except that the ink ingredients in Example 3 were replaced by the following ones.

(Preparation of Ink)

disperse solution used in Example 3	30 parts
triethylene glycol - monobutyl ether	0.8 part
glycerol	12 parts
diethylene glycol	15 parts
2-pyrrolidone	5 parts
ion-exchanged water	37.2 parts

Example 9

(Preparation of Pigment Dispersed Solution and Ink)

A pigment dispersed solution and ink were prepared exactly in the same manner as in Example 6 except that the dispersion resin was replaced by the polymer 4 polymerized above in the preparation of both the pigment dispersed solution and the ink in Example 6.

Example 10

(Preparation of Pigment Dispersed Solution and Ink)

A pigment dispersed solution and ink were prepared exactly in the same manner as in Example 7 except that the dispersion resin was replaced by the polymer 5 polymerized above in the preparation of both the pigment dispersed solution and the ink in Example 7.

Comparative Example 4

A pigment dispersed solution and ink were prepared exactly in the same manner as in Example 7 except that the dispersion resin was replaced by a styrene - maleic acid random copolymer SMA Resin 1440 (trade name, by ARCO chem. Co., acid value 175, weight-average molecular weight 2500) in Example 7.

Comparative Example 5

A pigment dispersed solution and ink were prepared exactly in the same manner as in Example 8 except that the dispersion resin was replaced by condensed sodium naphthalene sulfonate Roma D (trade name, by Sunnopuco Co., weight-average molecular weight 1800) in Example 8, and triethylene glycol - monobutyl ether was not added and replaced by ion-exchanged water during preparation of the ink.

Evaluation

The following tests were conducted by loading the ink thus prepared in an ink jet recording apparatus BJ-10V (trade name, by Canon Inc.) with an on-demand type recording multi-head in which a recording liquid is discharged by applying thermal energy corresponding to a recording signal.

Evaluation 1

15

Discharge stability of ink

Discharge stability of the ink was evaluated and marked to be any one of three ranks below by using the above ink jet recording apparatus:

- 20 O : good
 Δ : some parts disappear in solid printing area
 X : almost no discharge

Evaluation 2

25

Printing density of prints

Printing was made on copying paper of Xerox 4024 and Canon NP-DRY by using the above ink jet recording apparatus, and printing density of the prints was measured by Macbeth densitometer (TR918).

30

Evaluation 3

Quality evaluation of prints

35 Unevenness in printing density and sharpness of character edges of the prints were visually evaluated and marked to be any one of three ranks below:

- O : evenness in solid printing area was high and character edges were sharp
 Δ : character edges were sharp, but unevenness was found in solid printing area
 X : character edges were blurred and unevenness in solid printing area was significant

40 The evaluation results are listed in Table 2 below.

45

50

55

Table 2

	Evaluation Results			
	Evaluation 1 Discharge Stability	Evaluation 2 Printing Density		Evaluation 3 Printing quality
		Xerox4024	NP-DRY	
Example 6	O	1.34	1.51	O
Example 7	O	1.32	1.43	O
Example 8	O	1.36	1.52	O
Example 9	O	1.35	1.47	O
Example 10	O	1.36	1.48	O
Com. Ex.4	O	1.13	1.31	O
Com. Ex.5	Δ	0.95	1.19	Δ

As described hereinabove, the ink of the present invention has advantages, when applied to an ink jet printer utilizing thermal energy, such that printed images have good durability, the ink can always stably be discharged for a long period of time even under variations in driving conditions, and satisfactory printing quality and density are obtained on any type of plain paper while ensuring high reliability and stability during long-term storage.

Examples using polymer selected from the group (b) as dispersant

Example 11

(Manufacture of Ink)

(Preparation of Pigment Dispersed Solution)

styrene - vinyl acetate - acrylic acid copolymer (initial mol ratio in polymerization; 45:20:35, acid value 146, weight-average molecular weight 8800)	1.5 parts
monoethanolamine	1 part
ion-exchanged water	81.5 parts
diethylene glycol	5 parts

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 10 parts of new experimentally manufactured carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd., primary grain size 18 nm) and 1 part of isopropyl alcohol, followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 1. Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

5	above disperse solution	30 parts
	glycerol	2 parts
	diethylene glycol	15 parts
	N-methyl pyrrolidone	5 parts
	isopropyl alcohol	3 parts
10	Emulbon T-83 (organic boron-base surfactant, by Toho Chemicals Co., Ltd.)	0.5 part
	ion-exchanged water	44.5 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with monoethanolamine. The ink thus prepared was tested for later-described evaluation items by using an ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Example 12

20 (Manufacture of Ink)

(Preparation of Pigment Dispersed Solution)

25	styrene - maleic acid - allyl acetate copolymer (initial mol ratio in polymerization; 50:42:8, acid value 210, weight-average molecular weight 11000)	3 parts
	aminomethyl propanol	2 parts
	ion-exchanged water	75 parts
30	diethylene glycol	5 parts

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution was 15 parts of carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd., primary grain size 18 nm), followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 2. Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

40	above disperse solution	25 parts
	glycerol	8 parts
	ethylene glycol	5 parts
45	ethanol	5 parts
	ion-exchanged water	57 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with aminomethyl propanol, thereby obtaining ink.

The ink thus prepared was tested for later-described evaluation items by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Example 13

(Manufacture of Ink)

5 (Preparation of Pigment Dispersed Solution)

10	styrene - methacrylic acid - vinyl propionate copolymer (initial mol ratio in polymerization; 20:50:30, acid value 230, weight-average molecular weight 13000)	1.5 parts
	ion-exchanged water	81.5 parts
	ethylene glycol	5 parts

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 11 parts of new experimentally manufactured carbon black (S170 by Degussa AG, primary grain size 17 nm) and 1 part of isopropyl alcohol, followed by pre-mixing for 60 minutes. After that, the dispersion process was carried out under the same conditions as in Example 3. Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

20 (Preparation of Ink)

25	above disperse solution	30 parts
	glycerol	12 parts
	diethylene glycol	15 parts
	2-pyrrolidone	5 parts
	isopropyl alcohol	3 parts
30	Acetylenol EH (by Kawaken Fine Chemical Co., Ltd.)	0.3 part
	ion-exchanged water	34.7 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with monoethanolamine.

35 The ink thus prepared was tested for later-described evaluation items by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

40 Example 14

Ink was prepared exactly in the same manner as in Example 11 except that carbon black was replaced by Mogul L (by Cabot Co., primary grain size 24 nm), and was tested by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

45 Example 15

50 Ink was prepared exactly in the same manner as in Example 12 except that carbon black was replaced by Mogul L (by Cabot Co., primary grain size 24 nm), and was tested by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

The evaluation results are listed in Table 3 below. The evaluation items are the same as those used in Examples 1 to 5.

Table 3

Evaluation Results					
5		Evaluation 1 Printing Density		Evaluation 2 Number of sheets at non-discharge	Evaluation 3 Stability during storage
		Xerox4024	NP-DRY		
10	Example 11	1.23	1.32	no occurrence for 500 sheets	O
	Example 12	1.24	1.31	no occurrence for 500 sheets	O
	Example 13	1.27	1.35	no occurrence for 500 sheets	O
	Example 14	1.25	1.33	no occurrence for 500 sheets	O
15	Example 15	1.24	1.32	no occurrence for 500 sheets	O

As described hereinabove, the ink of the present invention has advantages, when applied to an ink jet printer utilizing thermal energy, such that printed images have good durability, the ink can always be stably discharged for a long period of time even under variations in driving conditions, and satisfactory printing quality and density are obtained on any types of plain paper while ensuring high reliability and stability during long-term storage.

Examples using polyethyleneimine as dispersant

Example 16

(Manufacture of Ink)

(Preparation of Pigment Dispersed Solution)

polyethyleneimine (Epomin SP-200, by Nippon Shokubai Co., Ltd., Mw 10000)	4 parts
ion-exchanged water	80 parts
diethylene glycol	5 parts

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 10 parts of carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd, primary grain size 18 nm) and 1 part of isopropyl alcohol, followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 1. Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

above disperse solution	30 parts
glycerol	5 parts
diethylene glycol	10 parts
N-methyl pyrrolidone	5 parts
isopropyl alcohol	3 parts
ion-exchanged water	47 parts

The ink thus prepared was tested by using an ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Example 17

(Manufacture of Ink)

5 (Preparation of Pigment Dispersed Solution)

10

polyethyleneimine (Epomin SP-300, by Nippon Shokubai Co., Ltd., Mw 30000)	5 parts
ion-exchanged water	75 parts
diethylene glycol	5 parts

15

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution was 15 parts of carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd., primary grain size 18 nm), followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 2. Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

20

(Preparation of Ink)

25

above disperse solution	25 parts
glycerol	8 parts
ethylene glycol	5 parts
ethanol	5 parts
ion-exchanged water	57 parts

30

The ink thus prepared was tested by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

35

Example 18

(Manufacture of Ink)

(Preparation of Pigment Dispersed Solution)

40

polyethyleneimine (Epomin SP-012, by Nippon Shokubai Co., Ltd., Mw 12000)	5 parts
ion-exchanged water	78 parts
ethylene glycol	5 parts

45

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 11 parts of new experimentally manufactured carbon black (S170 by Degussa AG, primary grain size 17 nm) and 1 part of isopropyl alcohol, followed by pre-mixing for 60 minutes. After that, the dispersion process was carried out under the same conditions as in Example 3. Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

50

55

(Preparation of Ink)

5	above disperse solution	30 parts
	glycerol	12 parts
	diethylene glycol	15 parts
	2-pyrrolidone	5 parts
	isopropyl alcohol	3 parts
10	Acetylenol EH (by Kawaken Fine Chemical Co., Ltd.)	0.3 part
	ion-exchanged water	34.7 parts

The ink thus prepared was tested by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Example 19

Ink was prepared exactly in the same manner as in Example 16 except that carbon black was replaced by Mogul L (by Cabot Co., primary grain size 24 nm), and was tested by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Example 20

Ink was prepared exactly in the same manner as in Example 17 except that carbon black was replaced by Mogul L (by Cabot Co., primary grain size 24 nm), and was tested by using the ink jet recording apparatus with an on-demand type recording multi-head in which ink is discharged by applying thermal energy corresponding to a recording signal.

Comparative Example 6

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as in Example 16 except that the dispersion resin was replaced by a styrene - acrylic acid - butyl acrylate random copolymer (acid value 135, weight-average molecular weight 5500) in Example 16.

Comparative Example 7

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as in Example 17 except that the dispersion resin was replaced by a styrene - maleic acid random copolymer SMA Resin 1440 (trade name, by ARCO chem. Co., acid value 175, weight-average molecular weight 2500) in Example 17.

Comparative Example 8

A pigment dispersed solution and ink were prepared and subjected to the printing test exactly in the same manner as in Example 18 except that the dispersion resin was replaced by condensed sodium naphthalene sulfonate Roma D (trade name, by Sunnopuco Co., weight-average molecular weight 1800) in Example 18.

Evaluation 1

Printing density of prints

Printing was made on copying paper Xerox 4024, copying paper Canon NP-DRY, FOX RIVER: PLOVER BOND paper, and Kokuyo report paper by using the above-described ink jet recording apparatus, and printing density of the prints was measured by Macbeth densitometer (TR918).

Evaluation 2

Printing was continuously made by using the above-described ink jet recording apparatus to check at which number sheet non-discharge of the ink occurred.

Evaluation 3

Stability during storage of ink

The above-prepared water-based ink was enclosed in a glass container and stored at 60 °C for six months. The ink which caused problems such as agglomeration of pigment particles and increase in viscosity after the storage period was marked X, and the ink which caused no problems was marked O.

Evaluation 4

Wiping resistance of prints

The above-prepared water-based ink was wiped with a finger 5 minutes after the printing. The ink with which the finger was not stained was marked O, the ink with which the finger was a little stained was marked Δ, and the ink with which the finger was thickly stained was marked X.

The evaluation results are listed in Table 4 below.

Table 4

Evaluation Results							
	Evaluation 1 Printing Density				2	3	4
	Xerox 4024	NP-DRY	Plover Bond	Kokuyo report			
Ex. 16	1.22	1.27	1.27	1.3	no occurrence for 500 sheets	O	O
Ex. 17	1.24	1.25	1.28	1.31	no occurrence for 500 sheets	O	O
Ex. 18	1.25	1.27	1.29	1.29	no occurrence for 500 sheets	O	O
Ex. 19	1.25	1.26	1.28	1.27	no occurrence for 500 sheets	O	O
Ex. 20	1.22	1.28	1.26	1.27	no occurrence for 500 sheets	O	O
Com. Ex. 6	1.1	1.32	1.21	1.24	no occurrence for 500 sheets	X	X
Com. Ex. 7	1.09	1.29	1.2	1.21	200 sheets	X	X
Com. Ex. 8	0.98	1.24	1.14	1.24	150 sheets	O	Δ
2: Evaluation 2 Number of sheets at non-discharge							
3: Evaluation 3 Stability during storage							
4: Evaluation 4 Wiping resistance							

As described hereinabove, the ink of the present invention has advantages, when applied to an ink jet printer utilizing thermal energy, such that printed images have good durability, the ink can always be stably discharged for a long period of time even under variations in driving conditions, and satisfactory printing quality and density are obtained on any types of plain paper and superior wiping resistance of prints is provided while ensuring high reliability and stability during long-term storage.

[Examples using white inorganic fine particles]

Example 21

5 (Preparation of Pigment Dispersed Solution)

10	styrene - acrylic acid - butyl acrylate copolymer (acid value 116, weight-average molecular weight 3700)	1.5 parts
	monoethanolamine	1 part
	ion-exchanged water	79 parts
	diethylene glycol	5 parts

15 The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 10 parts of new experimentally manufactured carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd., primary grain size 18 nm), 2.5 parts of surface-treated titanium dioxide (DS-4 by Idemitsu Kosan Co., Ltd., primary grain size 17 nm), and 1 part of isopropyl alcohol, followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 1.

20 Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

25

30	above disperse solution	30 parts
	diethylene glycol - monobutyl ether	0.5 parts
	glycerol	2 parts
	diethylene glycol	15 parts
	N-methyl pyrrolidone	5 parts
	ion-exchanged water	47.5 parts

35 The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with monoethanolamine, thereby obtaining the ink of the present invention.

Example 22

40 (Preparation of Pigment Dispersed Solution)

45	styrene - maleic acid half ester copolymer (acid value 200, weight-average molecular weight 12000)	4 parts
	aminomethyl propanol	2 parts
	ion-exchanged water	71 parts
	diethylene glycol	5 parts

50 The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 15 parts of carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd., primary grain size 18 nm) and 3 parts of surface-treated titanium dioxide (DS-4 by Idemitsu Kosan Co., Ltd., primary grain size 17 nm), followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 2.

55 Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

above disperse solution	20 parts
ethylene glycol - monobutyl ether	1 part
glycerol	8 parts
ethylene glycol	5 parts
ion-exchanged water	66 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with aminomethyl propanol, thereby obtaining ink.

Example 23

Ink was prepared exactly in the same manner as in Example 21 except that carbon black was replaced by Mogul L (by Cabot Co., primary grain size 24 nm).

Example 24

Ink was prepared exactly in the same manner as in Example 21 except that surface-treated titanium dioxide (IT-PC by Idemitsu Kosan Co., Ltd., primary grain size 60 nm) was used as the white inorganic fine particles.

Example 25

Ink was prepared exactly in the same manner as in Example 21 except that alumina fine particles (Aluminum Oxide C by Nippon Aerosil Co., Ltd., primary grain size 13 nm) was used as the white inorganic fine particles.

Example 26

(Preparation of Pigment Dispersed Solution)

Roma D (by Sunnopuco Co., sodium naphthalene sulfonate)	1.5 parts
ion-exchanged water	79.5 parts
ethylene glycol	5 parts

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 11 parts of new experimentally manufactured carbon black (S170 by Degussa AG, primary grain size 17 nm), 2 parts of surface-treated titanium dioxide (DS-4 by Idemitsu Kosan Co., Ltd., primary grain size 17 nm) and 1 part of isopropyl alcohol, followed by pre-mixing for 60 minutes. After that, the dispersion process was carried out under the same conditions as in Example 3.

Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

above disperse solution	30 parts
triethylene glycol - monobutyl ether	0.5 part
glycerol	12 parts
diethylene glycol	15 parts
2-pyrrolidone	5 parts
ion-exchanged water	37.5 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with monoethanolamine, thereby obtaining ink.

15 Reference Example 1

Ink was prepared in the same manner as in Example 21 except that diethylene glycol - monobutyl ether was not added and replaced by ion-exchanged water in the preparation of the ink in Example 21.

20 Reference Example 2

Ink was prepared in the same manner as in Example 22 except that the white inorganic fine particles were not added and replaced by ion-exchanged water in the preparation of the pigment dispersed solution in Example 22.

25 Reference Example 3

Ink was prepared in the same manner as in Example 23 except that diethylene glycol - monobutyl ether was not added and replaced by ion-exchanged water in the preparation of the ink in Example 23.

30 Reference Example 4

Ink was prepared in the same manner as in Example 26 except that the white inorganic fine particles were not added and replaced by ion-exchanged water in the preparation of pigment dispersed solution in Example 26.

Reference Example 5

40 Ink was prepared in the same manner as in Example 21 except that 2.5 parts, in terms of solid, of methyl polymethacrylate-base fine particles ME1000cf (by Soken Chemicals, Co., Ltd., primary grain size 450 nm, dispersed in water) was added in place of the white inorganic fine particles in the preparation of pigment dispersed solution in Example 21.

45

50

55

Evaluation

Evaluation was made similarly to Examples 6 to 10. The evaluation results are listed in Table 5 below.

Table 5

Evaluation Results				
	Evaluation 1 Discharge Stability	Evaluation 2. Printing Density		Evaluation 3 Printing quality
		Xerox4024	NP-DRY	
Example 21	O	1.35	1.47	O
Example 22	O	1.35	1.45	O
Example 23	O	1.38	1.52	O
Example 24	O	1.33	1.42	O
Example 25	O	1.32	1.39	O
Example 26	O	1.30	1.35	O
Ref. Ex. 1	Δ	1.28	1.38	Δ
Ref. Ex. 2	O	1.12	1.25	O
Ref. Ex. 3	Δ	1.30	1.42	Δ
Ref. Ex. 4	O	0.95	1.13	O
Ref. Ex. 5	Δ	1.15	1.29	O

Examples using rosin-denaturated maleic acid as dispersant

Example 27

(Preparation of Pigment Dispersed Solution)

Malkyd No. 32 (by Arakawa Chemicals Co., Ltd.)	1.5 parts
monoethanolamine	1 part
ion-exchanged water	81.5 parts
diethylene glycol	5 parts

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution were 10 parts of new experimentally manufactured carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd., primary grain size 18 nm) and 1 part of isopropyl alcohol, followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 1.

Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

5	above disperse solution	30 parts
	diethylene glycol - monobutyl ether	0.5 part
	glycerol	2 parts
	diethylene glycol	15 parts
	N-methyl pyrrolidone	5 parts
10	isopropyl alcohol	3 parts
	Emulbon T-83 (organic boron-base surfactant, by Toho Chemicals Co., Ltd.)	0.5 part
	ion-exchanged water	44.5 parts

15 The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with monoethanolamine, thereby obtaining the ink of the present invention.

Example 28

(Preparation of Pigment Dispersed Solution)

20

25	Hiparac C (by Nippon Shellac Co., Ltd.)	1 part
	aminomethyl propanol	2 parts
	ion-exchanged water	77 parts
	diethylene glycol	5 parts

30 The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution was 15 parts of carbon black (MCF 88 by Mitsubishi Chemical Industry Co., Ltd., primary grain size 18 nm), followed by pre-mixing for 30 minutes. After that, the dispersion process was carried out under the same conditions as in Example 2.

Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

35 (Preparation of Ink)

40	above disperse solution	25 parts
	ethylene glycol - monobutyl ether	0.8 part
	glycerol	9 parts
	ethylene glycol	5 parts
	ion-exchanged water	60.2 parts

45 The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with aminomethyl propanol, thereby obtaining ink.

Example 29

50 Ink was prepared exactly in the same manner as in Example 28 except that carbon black was replaced by Mogul L (by Cabot Co., primary grain size 24 nm).

55

Example 30

(Preparation of Pigment Dispersed Solution)

Malkyd No. 31 (by Arakawa Chemicals Co., Ltd.)	1.5 parts
ion-exchanged water	82.5 parts
ethylene glycol	5 parts

The above ingredients were mixed and heated to 70 °C using a water bath in order to completely dissolve the resin ingredient. Added to this solution was 11 parts of new experimentally manufactured carbon black (S170 by Degussa AG, primary grain size 24 nm), followed by pre-mixing for 60 minutes. After that, the dispersion process was carried out under the same conditions as in Example 3.

Further, the centrifugal separation process (12000 RPM, 20 minutes) was carried out to remove coarse particles, thereby preparing a disperse solution.

(Preparation of Ink)

above disperse solution	30 parts
triethylene glycol - monobutyl ether	0.5 part
glycerol	12 parts
diethylene glycol	15 parts
2-pyrrolidone	5 parts
ion-exchanged water	37.5 parts

The above ingredients were mixed and adjusted in pH value to fall in the range of 8 to 10 with monoethanolamine, thereby obtaining the ink of the present invention.

Reference Example 6

Ink was prepared in the same manner as in Example 27 except that diethylene glycol - monobutyl ether, as alkyl ether (with alkyl group having 4 or more carbons) of polyhydric alcohol according to the present invention, was not used and replaced by ion-exchanged water in the preparation of ink.

Reference Examples 7 and 8

Ink was prepared in the same manner as in Examples 28 and 29 except that Hiparac C, as rosin-denaturated maleic acid according to the present invention, was not added, but styrene - acrylic acid - butyl acrylate copolymer (acid value 110 / weight-average molecular weight 7000) was instead in the preparation of pigment dispersed solution.

Reference Example 9

Ink was prepared in the same manner as in Example 30 except that triethylene glycol - monobutyl ether was not used and replaced by ion-exchanged water in the preparation of ink.

Evaluation

Evaluation was made similarly to Examples 6 to 10. The evaluation results are listed in Table 6 below.

Table 6

Evaluation Results				
	Evaluation 1 Discharge Stability	Evaluation 2 Printing Density		Evaluation 3 Printing quality
		Xerox4024	NP-DRY	
Example 27	O	1.35	1.28	O
Example 28	O	1.38	1.32	O
Example 29	O	1.41	1.33	O
Example 30	O	1.40	1.32	O
Ref. Ex. 6	Δ	1.28	1.15	Δ
Ref. Ex. 7	O	1.30	1.25	Δ
Ref. Ex. 8	O	1.25	1.20	Δ
Ref. Ex. 9	Δ	1.20	1.15	Δ




As described hereinabove, the ink of the present invention has advantages, when applied to an ink jet printer utilizing thermal energy, such that printed images have good durability, the ink can always be stably discharged for a long period of time even under variations in driving conditions, and satisfactory printing quality and density are obtained on any types of plain paper while ensuring high reliability and stability during long-term storage.

While the present invention has been described with respect to what is presently considered to be the preferred embodiments, it is to be understood that the invention is not limited to the disclosed embodiments. To the contrary, the invention is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims. The scope of the following claims is to be accorded the broadest interpretation so as to encompass all such modifications and equivalent structures and functions.

Claims



1. A water-based ink comprising a pigment, a dispersant for dispersing said pigment, a water-soluble organic solvent, and water, wherein said dispersant is at least one compound selected from the group consisting of (a) to (c):

(a) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β - ethylenic unsaturated carboxylic acid,



where R is H or CH_3 , m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16;

(b) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),



where R_1 is H or CH_3 and R_2 is an alkyl group with 1 to 5 carbons; and
(c) polyethyleneimine.

2. A water-based ink according to claim 1, wherein said ink contains, as said dispersant, a polymer selected from said group (a) and, as said water-soluble organic solvent, at least one selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol.
3. A water-based ink according to claim 1, wherein the weight-average molecular weight of a polymer selected from said group (a) or (b) is in the range of 500 to 30000.
4. A water-based ink according to claim 1, wherein the weight-average molecular weight of a polymer selected from said group (a) or (b) is in the range of 1000 to 15000.
5. A water-based ink according to claim 1, wherein the content of a polymer selected from said group (a) or (b) is in the range of 0.1 to 5 wt% with respect to the total weight of the ink.
6. A water-based ink according to claim 1, wherein the monomer represented by said formula (IV) or (V) is selected from the group consisting of vinyl acetate, vinyl propionate, isopropenyl acetate, allyl acetate, allyl propionate, vinyl butyrate, and allyl butyrate.
7. A water-based ink according to claim 1, wherein the weight-average molecular weight of said polyethyleneimine is in the range of 1000 to 40000.
8. A water-based ink according to claim 1, wherein said ink contains said polyethyleneimine in the range of 0.1 to 10 wt% for the total weight of the ink.
9. A water-based ink according to claim 1, wherein said ink contains, as said organic solvent, at least one selected from the group consisting of methanol, ethanol, propanol, and butanol.
10. A water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol and dialkyl ether of triol, and white inorganic fine particles.
11. A water-based ink according to claim 10, wherein said white inorganic fine particles are titanium dioxide fine particles or alumina fine particles.

12. A water-based ink according to claim 10, wherein the ratio of primary particle size of said white inorganic fine particles to primary particle size of said pigment is in the range of 1/10 to 5/1.




13. A water-based ink according to claim 10, wherein the content ratio in weight of said white inorganic fine particles to said pigment is in the range of 1/20 to 1/1.

14. A water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains, as said water-soluble organic solvent, at least one selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol and dialkyl ether of triol, and as said dispersant, rosin-denaturated maleic acid.

15. An ink jet recording method comprising the step of:



ejecting droplets of ink containing a recording agent and a liquid medium from orifices of a recording head in accordance with a recording signal to thereby make a recording on a recording material, wherein said ink is a water-based ink comprising a pigment, a dispersant for dispersing said pigment, a water-soluble organic solvent, and water, wherein said dispersant is at least one compound selected from the group consisting of (a) to (c):

(a) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β - ethylenic unsaturated carboxylic acid,



where R is H or CH_3 , m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16;

(b) a polymer having a hydrophilic part and a hydrophobic part; said polymer containing, as a monomer making up said hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),






where R_1 is H or CH_3 and R_2 is an alkyl group with 1 to 5 carbons; and
(c) polyethyleneimine

16. An ink jet recording method according to claim 15, wherein said recording material is non-coated paper.

17. An ink jet recording method according to claim 15, wherein droplets of said ink are formed through thermal energy acting upon said ink.



18. A recording unit comprising an ink receptacle containing ink and a head portion for discharging said ink in the form of ink droplets, wherein said ink is a water-based ink comprising a pigment, a dispersant for dispersing said pigment, a water-soluble organic solvent, and water, wherein said dispersant is at least one compound selected from the group consisting of (a) to (c):

(a) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β -ethylenic unsaturated carboxylic acid,



where R is H or CH_3 , m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16;

(b) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),





where R_1 is H or CH_3 and R_2 is an alkyl group with 1 to 5 carbons; and
(c) polyethyleneimine

19. A recording unit according to claim 18, wherein said head portion includes a head for discharging the ink droplets through thermal energy acting upon said ink.

20. An ink cartridge comprising an ink receptacle containing ink, wherein said ink is a water-based ink comprising a pigment, a dispersant for dispersing said pigment, a water-soluble organic solvent, and water, wherein said dispersant is at least one compound selected from the group consisting of (a) to (c):



(a) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β -ethylenic unsaturated carboxylic acid,





where R is H or CH₃, m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16;

(b) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),






where R₁ is H or CH₃ and R₂ is an alkyl group with 1 to 5 carbons; and

(c) polyethyleneimine



21. An ink jet recording apparatus including a recording unit comprising an ink receptacle containing ink and a head portion for discharging said ink in the form of ink droplets, wherein said ink is a water-based ink comprising a pigment, a dispersant for dispersing said pigment, a water-soluble organic solvent, and water, wherein said dispersant is at least one compound selected from the group consisting of (a) to (c):

(a) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β -ethylenic unsaturated carboxylic acid,



where R is H or CH₃, m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16;

(b) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),





where R_1 is H or CH_3 and R_2 is an alkyl group with 1 to 5 carbons; and
(c) polyethyleneimine

22. An ink jet recording apparatus according to claim 21, wherein said head portion includes a head for discharging the ink droplets through thermal energy acting upon said ink.


23. An ink jet recording apparatus comprising a recording head for discharging ink droplets, an ink cartridge having an ink receptacle containing ink, and an ink supply portion for supplying said ink from said ink cartridge to said recording head, wherein said ink is a water-based ink comprising a pigment, a dispersant for dispersing said pigment, a water-soluble organic solvent, and water, wherein said dispersant is at least one compound selected from the group consisting of (a) to (c):

(a) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β -ethylenic unsaturated carboxylic acid,




where R is H or CH_3 , m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16;

(b) a polymer having a hydrophilic part and a hydrophobic part, said polymer containing, as a monomer making up said hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),



(IV)



(V)

where R_1 is H or CH_3 and R_2 is an alkyl group with 1 to 5 carbons; and
(c) polyethyleneimine

24. An ink jet recording apparatus according to claim 23, wherein said head is of a head for discharging the ink droplets through thermal energy acting upon said ink.
25. An ink jet recording method comprising the step of:
ejecting droplets of ink containing a recording agent and a liquid medium from orifices of a recording head in accordance with a recording signal to thereby make a recording on a recording material, wherein said ink is a water-based ink comprising a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains (i) at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and (ii) white inorganic fine particles.
26. An ink jet recording method comprising the step of:
ejecting droplets of ink containing a recording agent and a liquid medium from orifices of a recording head in accordance with a recording signal to thereby make a recording on a recording material, wherein said ink is a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and as said dispersant, rosin-denaturated maleic acid.
27. An ink jet recording method according to claim 25, wherein said recording material is non-coated paper.
28. An ink jet recording method according to claim 26, wherein said recording material is non-coated paper.
29. An ink jet recording method according to claim 25, wherein droplets of said ink are formed through thermal energy acting upon said ink.
30. An ink jet recording method according to claim 26, wherein droplets of said ink are formed through thermal energy acting upon said ink.
31. A recording unit comprising an ink receptacle containing ink and a head portion for discharging said ink in the form of ink droplets, wherein said ink is a water-based ink comprising a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains (i) at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and (ii) white inorganic fine particles.

32. A recording unit comprising an ink receptacle containing ink and a head portion for discharging said ink in the form of ink droplets, wherein said ink is a water-based ink a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and as said dispersant, rosin-denaturated maleic acid.
33. A recording unit according to claim 32, wherein said head portion includes a head for discharging the ink droplets through thermal energy acting upon said ink.
34. A recording unit according to claim 33, wherein said head portion includes a head for discharging the ink droplets through thermal energy acting upon said ink.
35. An ink cartridge comprising an ink receptacle containing ink, wherein said ink is a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains (i) at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and (ii) white inorganic fine particles.
36. An ink cartridge comprising an ink receptacle containing ink, wherein said ink is a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and as said dispersant, rosin-denaturated maleic acid.
37. An ink jet recording apparatus including a recording unit comprising an ink receptacle containing ink and a head portion for discharging said ink in the form of ink drop-lets, wherein said ink is a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains (i) at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and (ii) white inorganic fine particles.
38. An ink jet recording apparatus including a recording unit comprising an ink receptacle containing ink and a head portion for discharging said ink in the form of ink droplets, wherein said ink is a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and as said dispersant, rosin-denaturated maleic acid.
39. An ink jet recording apparatus comprising a recording head for discharging ink droplets, an ink cartridge having the ink receptacle containing ink, and an ink supply portion for supplying said ink from said ink cartridge to said recording head, wherein said ink is a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains (i) at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and (ii) white inorganic fine particles.
40. An ink jet recording apparatus comprising a recording head for discharging ink droplets, an ink cartridge having the ink receptacle containing ink, and an ink supply portion for supplying said ink from said ink cartridge to said recording head, wherein said ink is a water-based ink containing a pigment, a dispersant, a water-soluble organic solvent, and water, wherein said ink contains at least one water-soluble organic solvent selected from the group consisting of monoalkyl ether of diol, monoalkyl ether of triol, and dialkyl ether of triol, and as said dispersant, rosin-denaturated maleic acid.

FIG. 1 (a)




FIG. 1 (b)




FIG. 2




FIG. 3




FIG. 4





FIG. 5



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 622 429 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **94106082.4**(51) Int. Cl.⁶: **C09D 11/00, B41J 2/01**(22) Date of filing: **19.04.94**

(30) Priority: **26.04.93 JP 99527/93**
26.04.93 JP 99528/93
10.05.93 JP 108233/93
18.05.93 JP 116077/93

(43) Date of publication of application:
02.11.94 Bulletin 94/44

(84) Designated Contracting States:
AT BE CH DE DK ES FR GB GR IE IT LI LU NL
PT SE

(88) Date of deferred publication of the search report:
25.10.95 Bulletin 95/43

(71) Applicant: **CANON KABUSHIKI KAISHA**
30-2, 3-chome, Shimomaruko,
Ohta-ku
Tokyo (JP)




(72) Inventor: **Kashiwazaki, Akio, c/o Canon**

Kabushiki Kaisha
3-30-2, Shimomaruko,
Ohta-ku
Tokyo (JP)
Inventor: **Suga, Yuko, c/o Canon Kabushiki**
Kaisha
3-30-2, Shimomaruko,
Ohta-ku
Tokyo (JP)
Inventor: **Takaide, Aya, c/o Canon Kabushiki**
Kaisha
3-30-2, Shimomaruko,
Ohta-ku
Tokyo (JP)

(74) Representative: **Weser, Wolfgang**
Dres. Weser & Martin,
Patentanwälte,
Radeckestrasse 43
D-81245 München (DE)


(54) **A water-based ink, ink jet recording method using same, and equipment using same.**

(57) A water-based ink containing a pigment, a dispersant for dispersing the pigment, a water-soluble organic solvent, and water. The dispersant used is at least one compound selected from the groups (a) to (c): (a) a polymer having a hydrophilic part and a hydrophobic part, the polymer containing, as a monomer making up the hydrophilic part, 3 to 25 mol% of at least one monomer containing a long-chain nonionic group, which is selected from the following formulae (I) to (III), and 5 to 60 mol% of α , β - ethylenic unsaturated carboxylic acid,




where R is H or CH_3 , m and n are each a numeral from 2 to 24, l is a numeral from 1 to 12, p is a numeral from 1 to 12, and q is a numeral from 1 to 16; (b) a polymer having a hydrophilic part and a hydrophobic part, the polymer containing, as a monomer making up the hydrophobic part, 5 to 70 mol% of at least one monomer selected from the following formulae (IV) and (V),

EP 0 622 429 A3



(IV)



(V)

where R_1 is H or CH_3 and R_2 is an alkyl group with 1 to 5 carbons; and (c) polyethyleneimine. The ink may be used in an apparatus and according to the present ink jet recording method.

FIG. 1 (a)





FIG. 1 (b)





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 94 10 6082

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.5)
X	US-A-5 085 698 (MA ET AL) * column 3, line 23 - column 9, line 23; claims *	1-6,9,10	C09D11/00 B41J2/01
X	XEROX DISCLOSURE JOURNAL, vol.12, no.4, August 1987, ROCHESTER,NY, USA page 169 KANG 'INK JET PRINTING METHOD FOR HIGH WATERFASTNESS AND LIGHTFASTNESS ON PRINTED IMAGES'	1	
X	US-A-4 197 135 (BAILEY ET AL) * column 1, line 16 - column 2, line 68; claim 1 *	1,7,8	
X	EP-A-0 068 903 (KONISHRIKU PHOTO) * page 10, line 10 - page 19, line 122; claims 1,4,7,8; example 2 *	1	
P,X	EP-A-0 581 135 (CANON) * page 9, line 52 - page 10, line 58; claims *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.5) C09D
A	EP-A-0 514 159 (XEROX) * page 3, line 32 - page 4, line 23; claims 1,2,4 *	2	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 30 August 1995	Examiner Bourgonje, A
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

THIS PAGE BLANK (USPTO)